

Bureau of Standards

Certificate of Analyses

OF

STANDARD SAMPLE No. 32a

CHROME-NICKEL STEEL

ANALYST	CAR- BON	SILICON		PHOS- PHOR- US	SULPHUR		MANGANESE		CHROMIUM		NICKEL		COP- PER
	DIRECT COMBUS- TION	SULPHURIC ACID DEHYDRATION	OTHER METHODS	ALKALI- MOLYBDATE	GRAVIMETRIC (DIRECT OXIDATION)	EVOLUTION (ZnS-KI-KIO ₃)	BISMUTHATE	OTHER METHODS	PERFULPHATE OXIDATION	OTHER METHODS	WEIGHING NICKEL-DI- METHYL GLY- OXIME	OTHER METHODS	Cu S-Cu O
1.....	0.400	0.114		{0.021 ^r 0.021	0.016	0.018	0.240		0.890	0.90 ^a	1.56		0.068
2.....	.380	.123		.020	.019		.250		.891		1.53		.060
3.....	.389	.103	0.108 ^b	.020	.017	.018	.239		.873	.88 ^a	1.57		.081
4.....	.414	.119		.018		{.018 ^c .018		0.27 ^d		.89 ^e		1.59	
5.....	.37		.112 ^f	.021	.015	.021 ^g	.255	.255 ^h	.890	.905 ⁱ	1.58	1.57 ^j	.083 ^k
6.....	{.41 ^l .40		.12 ^b	.021		.020 ^g	.27 ^m			.89 ^e		1.58 ^j	.08 ⁿ
7.....	.385	.112		.019	.020	.018	.231		.912	.910 ^a	1.56		.061
8.....	.39	.105	.085 ^o	.019		{.018 ^g .018	.238	.246 ^p	.88		1.53	1.63 ^j	.06
9.....	.391	.111		.018	.015	.014	.245		.88		1.58		.07 ^k
10.....	.409	.114		.022	.018	.015 ^g	.227		.849	.846 ^e		1.58 ^j	.068 ⁿ
11.....	.400	.110		{.017 ^r .018	.016	.016	.258	.252 ^q		.859 ^e	1.54		.082
12.....	.384	.113	.107 ^b	.020	.018		.231		.903		1.59		.089
13.....	.423		.102 ^b	.020	.018	.017 ^g	.24			.882 ^s	1.52		.094
14.....	.388	.113		{.019 ^t .020	.017	.016	.225	.235 ^p	.865		1.57	1.57 ^j	.08 ^k
AVERAGE	0.396	0.112	0.106	0.020	0.017	0.018	0.242	0.252	0.883	0.885	1.56	1.59	0.075
GENERAL AVERAGE.....	0.396	0.110		0.020	0.017*	0.018	0.244		0.884†		1.57		0.075

* Recommended value.

† Recommended value, 0.89.

^a B. S. Hydrolysis and fusion method.^b Drown's method.^c Evolution in H+HCl vapor at 950° C. to 1,000° C.^d PbO₂-arsenite.^e Permanganate oxidation.^f HCl-HNO₃ solution.^g Absorbed in ammoniacal CdCl₂.^h Electrometric titration with HgNO₃ after bismuthate oxidation.ⁱ Electrometric titration.^j Final KCN titration.^k Na₂S₂O₃ precipitation—CuS—CuO.^l Returned.^m Bismuthate-arsenite.ⁿ Na₂S₂O₃-electrolysis.^o Solution in HCl-HNO₃-H₂SO₄.^p Persulphate-arsenite.^q William's method.^r Filtered before addition of Molybdate.^s KClO₃ oxidation.^t Weighing yellow precipitate.

INDEX TO ANALYSTS

1. J. I. Hoffman, Bureau of Standards.
2. L. F. Witmer, Bureau of Standards.
3. Routine Laboratory, Bureau of Standards, H. A. Bright in charge.
4. C. M. Johnson, The Crucible Steel Co. of America, Pittsburgh, Pa.
5. G. L. Kelley, Nicetown Laboratory, Midvale Steel and Ordnance Co., Philadelphia, Pa.
6. H. C. Parish, Arthur D. Little, Inc., Cambridge, Mass.
7. G. W. Angell, Research Department, Hydraulic Steel Co., Cleveland, Ohio.

8. Rodney Snay, The Timken Roller Bearing Co., Canton, Ohio.
9. William Brady, Illinois Steel Co., South Chicago, Ill.
10. Alma Johnson, Atchison, Topeka & Santa Fe Railway, Chicago, Ill.
11. A. M. Smoot, Ledoux & Co., New York City, N. Y.
12. Paul L. Tyson, The Carpenter Steel Co., Reading, Pa.
13. J. V. Emmons, The Cleveland Twist Drill Co., Cleveland, Ohio.
14. W. D. Brown, The Carnegie Steel Co., Pittsburgh, Pa.